



Deutsches Zentrum
DLR für Luft- und Raumfahrt e.V.
German Aerospace Center



Toward Modeling Thermal Runaway of Li-ion Batteries

N. Tanaka, M. Hedwig, C. Hellwig and W.G. Bessler
Institute of Technical Thermodynamics, German Aerospace Center (DLR), Stuttgart, Germany
Helmholtz Institute Ulm for Electrochemical Energy Storage (HIU), Ulm, Germany

Introduction and motivation

Thermal runaway of lithium batteries is major issue for development of high-power cells. We present preliminary numerical study of the runaway extreme event in **LiFePO₄/graphite cells** initiated via thermal decomposition of the solid electrolyte interface (SEI) layer. The approach is based on a multi-scale model from nano-scale to macro-scale and includes global electrochemical and thermochemical kinetics as implemented into the in-house software DENIS.

Multi-scale model

Transport

The model includes three transport regimes at three different scales. Each scale is modeled in 1D. Solved in DENIS. [1],[2]

~20 mm scale

Heat transport


$$\frac{\partial(\rho C_p T)}{\partial t} = \frac{\partial}{\partial y} \left(\lambda \frac{\partial T}{\partial y} \right) + \dot{Q}_{\text{elchem}} + \dot{Q}_{\text{ohm}}$$



~100 μm scale

Lithium ion charge transport in electrolyte


$$\frac{\partial(c c_i)}{\partial t} = \frac{\partial}{\partial y} \left(D_i(c_i, T) \frac{\partial c_i}{\partial y} \right) + \frac{z F}{R T} \frac{\partial}{\partial y} \left(D_i(c_i, T) c_i \frac{\partial \phi}{\partial y} \right) + M_i S_i^y$$



~100-1000 nm scale

Lithium ion transport

$$\frac{\partial \rho_{Li}}{\partial t} = \frac{1}{r^2} \frac{\partial}{\partial r} \left(r^2 D \frac{\partial \rho_{Li}}{\partial r} \right) - \frac{M_{Li}}{z F} i$$



Kinetics

In addition to transport, electrochemical kinetics is considered in the model. Solved in DENIS.

Butler-Volmer equation


$$i = i_0 \left(\exp \left(\frac{\alpha F}{R T} (\eta_{\text{act}} - R_{\text{SEI}} \cdot i) \right) - \exp \left(- \frac{(1-\alpha) F}{R T} (\eta_{\text{act}} - R_{\text{SEI}} \cdot i) \right) \right)$$

Overpotential


$$\begin{cases} \text{Activation} & \eta_{\text{act}} = \Delta \phi(t) - \Delta \phi_{\text{eq}}(c_{Li}) - \eta_{\text{conc}} \\ \text{Concentration} & \eta_{\text{conc}} = \frac{R T}{z F} \ln \left(\frac{c_0}{c(t)} \right) \end{cases}$$

Thermal decomposition model

Modeling Procedure



SEI decomposition



The exothermic SEI decomposition reaction is calculated based on the above reaction equation through CANTERA [3].


Parameters [4]

| | |
|---|-------------------------|
| Pre-exponential factor [s ⁻¹] | 7.88 × 10 ³⁶ |
| Activation energy [J/mol] | 2.81 × 10 ⁵ |
| Heat of reaction [J/g] | 257 |

Validation of heat transport model

Model is valid > 273 K and < 5C.
Bulk diffusion neglected here.


Good agreement with experiment at 293 K, 1C.
Reversible heat dominates in temperature profile.



Thermal runaway simulation

DSC simulations are conducted and compared with a result by Spotnitz et al. [4]

Thermal runaway is successfully observed at extreme condition under low heat transfer coefficient and thermal conductivity.



Conclusion

- Developed multi-scale thermal battery model
- The heat transport model is validated in wide range of operating conditions

- Simulated a DSC curve of SEI decomposition and successfully reproduce curve by Spotnitz et al.
- Conducted first thermal runaway simulation

[1] W. G. Bessler, S. Gewies and M. Vogler, Electrochimica Acta 53 (2007) 1782 - 1800

[2] J. Neidhardt, Journal of Electrochemical Society (2012) submitted

[3] D. G. Goodwin, <http://code.google.com/p/cantera> (2001-2010)

[4] R. Spotnitz and J. Franklin, Journal of Power Sources 113 (2003) 81-100